POLYKEN®

1111

FR Double-Sided Carpet Tape

Release Liner	Carrier	: Polye	ester Film			
Adhesive 1 (H	ligh) Adhesi	ve: Diffe	Differential, Proprietary Blends			
Carrier	Liner:	Whit	White Kraft			
Adhesive 2 (Low) *Other	*Other color and liner options may be available.				
	Specifi	cations:	Meets FAR 25.853(a), BMS5-133F Type IV, Class 1 Airbus ABD0031, Para 7.3.2			
	Standa	rd Sizes:	2" x 60Yd (Other sizes may be available upon request)			
	Арр	lications				
 Carpet & non-textile flooring installa and stairs of aircraft Features 	ation on interior floo	rs ● Gene	Benefits			
Differential Adhesive		 Clean removal from most surfaces Aggressive bond for secure hold 				
Antimony Trioxide, Halogen, Bromide Free			 Repositionable adhesive for easy installation Environmentally-friendly 			
 Antimony movide, halogen, bronnde riee Flame Retardant 			 Meets FAA requirements for use in aircraft 			
ightweight Construction • Improved efficiency						
Lightweight construction		• mpr	loved enciency			
	Physica	l Propertie	es			
	Standard UOM	Metric UO	DM Test Method			
otal Thickness*	3.9 mils	99 mic	c ASTM D-1000			
Adhesion to Steel (Adhesive 1)	7.88 lb/in	34.5 N/25i	mm ASTM 3330 Meth. B			

Total Thickness*	3.9 mils	99 mic	ASTM D-1000
Adhesion to Steel (Adhesive 1)	7.88 lb/in	34.5 N/25mm	ASTM 3330 Meth. B
Adhesion to Steel (Adhesive 2)	2.63 lb/in	11.5 N/25mm	ASTM 3330 Meth. B
Adhesion to AL (Adhesive 1)	7.81 lb/in	34.25 N/25mm	ASTM 3330 Meth. B
Adhesion to AL (Adhesive 2)	2.81lb/in	12.3 N/25mm	ASTM 3330 Meth. B
Tensile Strength	27 lb/in	118.2 N/25mm	ASTM D-1000
Weight	4.5 oz/sq yd	152.6 g/m²	ASTM D-1000

*Does not include release liner

Recommended Storage Conditions: 40-60% Humidity, 60°F-80°F Standard Shelf Life (at 25C): 36 months from date of manufacture.

The information presented herein was prepared at BERRY PLASTICS CORPORATION (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To Berry Plastics' knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY PLASTICS assumes any legal responsibility.



25 Forge Pkwy Franklin, MA 02038 1-800-343-7875 Fax 1-800-328-4822 www.berryplastics.com Nijverheidsstraat 10 2260 Oevel (Westerlo) Belgium 32-014-722500 Fax 32-014-722570 8/13/13